

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-275275

(43)Date of publication of application : 30.09.1994

(51)Int.CI. H01M 4/58 H01M 4/02 H01M 10/40

(21)Application number : 05-084134 (71)Applicant : SANYO ELECTRIC

(22)Date of filing : 17403.1993 (72)Inventor : MAYUMI UEHARA

TOSHIYUKI NOMA

HIROSHI KURIKAWA

CLAIMS

[Claim(s)]

[Claim 1] The nonaqueous battery characterized by using metal multiple oxide expressed by empirical formula $Li_xByNi_zCo_wO_a$ (wherein, $0 < x < 1.3$, $y > 0$, $0 \leq w \leq z$, $y+z+w=1$, and $1.8 \leq a \leq 2.2$) as a positive active material in the nonaqueous battery using the material which can intercalate or de-intercalate lithium ion or lithium métal

[Claim 2] The nonaqueous battery according to claim 1 whose y in the aforementioned empirical formula is 0.01-0.3.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0006] [The purpose of this invention]

To offer the highly safety nonaqueous battery which seldom carries out unusual generation of heat even when cell temperature rises, since the reaction start temperature of a positive active material and the electrolytic solution is high.

[0015] (Example 1)

The flat type nonaqueous battery (this invention cell) was produced.

[0016] [Production of positive electrode]

$LiOH$, B_2O_3 , $Ni(OH)_2$, $Co_2(OH)$ are mixed at the rate of the atomic ratio $1.0 : 0.01 : 0.5 : 0.49$.

It was calcinated at 800 degree C for 20 hours, and is empirical formula $LiB_{0.01}Ni_{0.5}Co_{0.49}O_2$.

[0017] Subsequently, this cathode powder, the acetylene black as an electric conductive agent, and the fluoriné resin powder as a binder were mixed at $90 : 6 : 4$. It was pressed at $2 t/cm^2$,

AM2

and was dried at 250 degree C. The disc-like positive electrode with a diameter of 20mm was produced. In addition, the stainless steel plate (SUS304) was used as positive-electrode current collection field.

[0023] (Example 2)

Empirical-formula $\text{LiB}_{0.1}\text{Ni}_{0.5}\text{Co}_{0.4}\text{O}_2$

[0024] (Example 3)

Empirical-formula $\text{LiB}_{0.20}\text{Ni}_{0.5}\text{Co}_{0.3}\text{O}_2$

[0025] (Example 4)

Empirical-formula $\text{LiB}_{0.30}\text{Ni}_{0.5}\text{Co}_{0.2}$

[0026] (Example 5)

Empirical-formula $\text{LiB}_{0.35}\text{Ni}_{0.5}\text{Co}_{0.1}$


[0027] (Example of a comparison)

Empirical-formula $\text{LiNi}_{0.5}\text{Co}_{0.5}\text{O}_2$

[Drawing 2]

[Drawing 3]

Onset temperature of exothermic reaction



Discharge Capacity

